



Unit 9, Stanford Business Park
 16th Road Midrand
www.hayfordtraders.co.za

DOCRIL

Properties:	Specification:	Test Method:
Composition	100% solution dyed acrylic	
Coating	Water Repellent Finish	
Construction	Plain Weave	
Weight (gsm)	295	UNE 53423
Spray Test	90	UNE 24920
Tensile Strength (daN)		
Warp	125	ISO 13934
Weft	70	
Tearing Strength (daN)		
Warp	5	DIN 5035-90
Weft	3	
Usable Width (cm)	120	
Water Column (mm)	300	UNE 20811
Oil Test	5	AATCC 118
UPF Rating	50+	UV AS/NZS 4399:1996

WARRANTY: during this period, it covers any abnormal deterioration of the physical properties and colour of the Docril fabric, given that maintenance advice has been properly followed.

MAINTENANCE: To achieve a longer life expectancy and a better look of the fabrics, we suggest cleaning your Docril fabric with a soft bristle brush and rinsing with water. For localised stains clean with a neutral detergent mixed with lukewarm water (maximum 40°C) and then rinse. The fabric must be left to dry completely before it is rolled up. If the awning has to be rolled up when the fabric is still wet, this can be air dried but never hot dried, although the fabric due to its technical characteristics, dries very fast itself.

Please note that the information shared in this document is for general information only and it is the responsibility of the customer to ensure that this product meets their specific requirements. The data in this document is for indication only and the product performance properties may vary. This document is not to be treated as a Certificate of Conformance. Hayford Traders will not entertain any damages claimed against them as a result of data expressed in this document.