



Unit 9, Stanford Business Park  
 16th Road Midrand  
[www.hayfordtraders.co.za](http://www.hayfordtraders.co.za)

**ENDURER COTTON CANVAS  
 SABS 495 COMPLIANT**

SABS 495 refers to a set of specifications relating to:  
 Water and Oil Repellent Effects.  
 Tensile Strength.  
 Fastness of Colour to Light, Water and Rubbing.

Properties:	Specification:	Test Method:
<b>Composition</b>	100% Cotton	N/A
<b>Construction</b>	3 Ply Plain Weave	N/A
<b>Water Penetration (mm)</b>		
Hydrostatic Pressure Test	306	DIN EN 20811
<b>Weight (gsm)</b>	510	
<b>Usable Width (cm)</b>	158	
<b>Tensile Strength</b>		
Maximum Force (N)		
Warp	1786	DIN EN ISO/SANS ISO 13934-1
Weft	936	
<b>Colour Fastness to Light</b>		
Xenon Arc Fading Lamp Test	4	ISO 105-B02:1997
<b>Colour Fastness to Perspiration</b>		
Acid (change of colour shade)	4-5	DIN EN ISO 105-E04
Alkaline (change of colour shade)	4-5	
<b>Colour Fastness to Rubbing</b>		
Staining of Transfer Cloth		
Dry	4-5	DIN EN ISO 105-X12
Wet	3-4	
<b>Colour Fastness to Water</b>		
Change of colour	4-5	DIN EN ISO 105-E01
<b>Oil Repellency</b>	6	AATCC 118/EN 14419
<b>Water Repellency</b>	90	AATCC 22/EN 24920

**Cleaning instruction:** If the canvas is affected due to heavy staining in a specific spot, it can be cleaned with a soft brush and warm water. Tougher stains can be cleaned with a very diluted soap water solution of at least 20 parts water to 1 part soap. Please do not use chemicals, bleach or harsh astringents on the canvas as it could affect the finishes. Care should be taken to ensure the canvas is not dragged on rough surfaces.

Please note that the information shared in this document is for general information only and it is the responsibility of the customer to ensure that this product meets their specific requirements. The data in this document is for indication only and the product performance properties may vary. This document is not to be treated as a Certificate of Conformance. Hayford Traders will not entertain any damages claimed against them as a result of data expressed in this document.