



Unit 9, Stanford Business Park
 16th Road Midrand
www.hayfordtraders.co.za

TRAMPOLINE

| Properties: | Specification: | Test Method: |
|-------------------------------------|---------------------|----------------------------------|
| | | |
| Composition | 100% Poly Propylene | N/A |
| Weight (gsm) | 255 | |
| Usable Width (cm) | 394 | |
| Tensile Strength (kgf) | | |
| Warp | 247.9 | ASTM D5034-09 (2013) Grab Method |
| Filling | 204.7 | |
| Ball Bursting Strength (kgf) | 246.90 | Modified ASTM D3787-07 |
| Tearing Strength | | |
| Across Warp | 59.0 | ASTM D2261-13/Tongue Tear |
| Across Filling | 55.0 | |

Please note that the information shared in this document is for general information only and it is the responsibility of the customer to ensure that this product meets their specific requirements. The data in this document is for indication only and the product performance properties may vary. This document is not to be treated as a Certificate of Conformance. Hayford Traders will not entertain any damages claimed against them as a result of data expressed in this document.